Application

Upholstery

Contents

60% Rayon, 40% Polyster, Viscose Rayan Pile Velvet

Width

54"

Repeat

App. 0.75" H

Roll Length

App. 40yds

General Characteristics

Superior wear resistance : Exceeds 100,000 rubs (ASTM D4157 Wyzenbeek)†

Meet or Exceeds All ACT Heavy Duty Performance Guideline for Upholstery

Colorfastness to light (AATCC-16/passes)

Colorfastness to crocking (AATCC-8/passes)

Flammability

CA Bulletin 117 - 2013

UFAC / NFPA - 260

Motor Vehicle Safety Standard - 302

IMO A652 (16) 8.2

Care & Cleaning

Cleaning Code: S

- + All stains and spills should be addressed Immediately. The longer it remains, The more difficult it will be to remove.
- + A professional furniture cleaning service is recommended.
- + Always test on an inconspicuous area first.

Warranty

Please refer to our Terms of Sales for warranty information.

† Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.



Night shade

